AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the

application:

Claim 1 (currently amended): An impact modified thermoplastic olefin composition consisting

essentially of a blend of one or more polyolefin homopolymer resins, from about 17% by weight

to about 30% by weight of one or more rubbery copolymers comprising at least one alpha olefin,

and from about 1.0% to about 8.0% by weight of one or more nonionic surfactants[[.]], and

mineral oil or polybutene, provided that the mineral oil or polybutene is present in an amount

that does not exceed 8% by weight.

Claim 2 (canceled)

Claim 3 (original): The impact modified thermoplastic olefin composition according to claim 1

wherein the polyolefin homopolymer resin is a polypropylene homopolymer.

Claim 4 (original): The impact modified thermoplastic olefin composition according to claim 1

wherein the nonionic surfactant is selected from the group consisting of ethoxylated ethers,

ethoxylated alkylphenols, ethoxylated aryl phenols and ethoxylated sorbitan fatty acid esters.

Claim 5 (original): The impact modified thermoplastic olefin composition according to claim 1

wherein the nonionic surfactant is selected from the group consisting of polyoxyethylene

sorbitan monolaurate, polyoxyethylene sorbitan monopalmitate, polyoxyethylene sorbitan

monostearate, polyoxyethylene sorbitan tristearate, polyoxyethylene sorbitan monooleate and

polyoxyethylene sorbitan trioleate.

Claim 6 (canceled)

Application No.: 10/668,041

Amendment Dated: October 31, 2005 Reply to Office action of: July 5, 2005

Page 3

Claim 7 (currently amended): The impact modified thermoplastic olefin composition according

to claim 6 5 wherein the ethoxylated sorbitan fatty acid ester nonionic surfactant is

polyoxyethylene sorbitan trioleate.

Claim 8 (currently amended): The impact modified thermoplastic olefin composition according

to claim 6 1 having an instrumented impact strength at -30°C. of 100 in-lbs or greater as

measured in accordance with ASTM D 5420 and a flexural modulus of 1.4 x 10⁵ psi or greater as

measured in accordance with ASTM D 790.

Claims 9 - 11 (cancelled)